

## **Working & Curing: 68F (20C)**

Useable life – 35mins. at 68F

Touch Dry – 8 hours at 68F

Hard Dry – 16 hours at 68F

Minimum over coating:

6 hours at 68F

Maximum over coating:

12 hours at 68F

*Cooler temps = longer time*

*Warmer temps – shorter time*

Cures down to 35F in high  
humidity environments.



**Sea Tech & Fun USA**  
[www.spadeanchorusa.com](http://www.spadeanchorusa.com)

## **Anchor Refinishing Kit**

Make your rusty anchor look  
new again. Faster and less  
expensive than re-galvanizing.

*Do it yourself!*

**NON-FLAMMABLE**

**EXCELLENT  
CORROSION  
RESISTANCE**

**HIGH ADHESION**

**LONG TERM  
PROTECTION**

Quart kits cover 53 sq. ft  
at 6 mils dry  
film thickness.

**Kits can be ordered from:**

**Sea Tech & Fun USA**  
[seatechandfunusa@yahoo.com](mailto:seatechandfunusa@yahoo.com)  
[www.spadeanchorusa.com](http://www.spadeanchorusa.com)



**Sea Tech & Fun  
USA**

# **ANCHOR REFINISHING KIT**

**The Solution to Rusty An**



**Sea Tech & Fun USA**  
[www.spadeanchorusa.com](http://www.spadeanchorusa.com)  
**(321) 409 – 5714**

Our anchor refinishing kit is made from a high grade, two part, 100% epoxy with anti-corrosion resistance filters, to be used for any environment. It can be applied over manually or mechanically prepared surfaces to provide a primer or top coat for rusty surfaces. It can be easily applied by brush or roller to achieve a 6 to 12 mils dry film thickness.

Our anchor refinishing kit is a non flammable, high adhesion and anti-corrosion resistant material. You can partially mix the system or mix the entire unit. This product cures down to 35F in high humidity environments.

### **Preparation**

Remove all oil, grease and wire brush, grind or sand blast anchor. Apply three coats to the entire anchor.

### **Mixing and Application**

Mixing Ratio: 3 to 1 by volume

Color: Silver Grey

Non Flammable

Clean up tool: MEK or Toluene

Percent Solids: 100%



### **Caution**

Can cause skin and eye irritation. Avoid contact with skin, eyes, and clothing. Consult MSI for more information.

### **Important**

Follow all instructions  
Mix 3 to 1 by volume.  
Apply three coats to all surfaces of the anchor.  
You can partially mix contents of the kit.

Color: Silver Grey